



# Nylon 12™

## MATERIAL DATA SHEET



Nylon 12™ is a semi-crystalline thermoplastic. It offers up to five times greater resistance to breaking and better impact strength compared to even the strongest FDM materials. It has high fatigue resistance and strong chemical resistance. Nylon 12 is primarily used in aerospace, automotive and consumer goods industries to take on everything from tooling, jigs and fixtures to covers, panels and vibration resistant components. Unparalleled toughness and a simple, clean process – free of powders.

*Quick Facts:*

- 5x greater resistance than other FDMs
- Semi-crystalline structure is chemical resistant and strong
- Free of powders



*Color options:*

Black

CONDITIONED\*

MECHANICAL PROPERTIES	TEST METHOD	ENGLISH		METRIC	
		XZ AXIS	ZX AXIS	XZ AXIS	ZX AXIS
Tensile Strength, Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	4,600 psi	4,100 psi	32 MPa	28 MPa
Tensile Strength, Ultimate (Type 1, 0.125", 0.2"/min)	ASTM D638	6,650 psi	5,600 psi	46 MPa	38.5 MPa
Tensile Modulus (Type 1, 0.125", 0.2"/min)	ASTM D638	186,000 psi	165,000 psi	1,282 MPa	1,138 MPa
Elongation at Break (Type 1, 0.125", 0.2"/min)	ASTM D638	30%	5.4%	30%	5.4%
Elongation at Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	2.4%	2.7%	2.4%	2.7%

# Nylon 12™

## CONDITIONED\*

Continued MECHANICAL PROPERTIES	TEST METHOD	ENGLISH		METRIC	
		XZ Axis	ZX Axis	XZ Axis	ZX Axis
Flexural Strength (Method 1, 0.05"/min)	ASTM D790	9,700 psi	8,800 psi	67 MPa	61 MPa
Flexural Modulus (Method 1, 0.05"/min)	ASTM D790	185,000 psi	171,000 psi	1,276 MPa	1,180 MPa
Flexural Strain at Break	ASTM D790	No Break	>10%	No Break	>10%
IZOD impact - notched (Method A, 23°C)	ASTM D256	2.5 ft-lb/in	1 ft-lb/in	135 J/m	53 J/m
IZOD impact - unnotched (Method A, 23°C)	ASTM D256	31 ft-lb/in	3.7 ft-lb/in	1,656 J/m	200 J/m
Compressive Strength, Yield (Method 1, 0.05"/min)	ASTM D695	7,400 psi	7,900 psi	51 MPa	55 MPa
Compressive Strength, Ultimate (Method 1, 0.05"/min)	ASTM D695	24,200 psi	800 psi	167 MPa	6 MPa
Compressive Modulus (Method 1, 0.05"/min)	ASTM D695	730,000 psi	155,000 psi	5,033 MPa	1,069 MPa

## UNCONDITIONED (DRY)\*\*

MECHANICAL PROPERTIES	TEST METHOD	ENGLISH		METRIC	
		XZ AXIS	ZX AXIS	XZ AXIS	ZX AXIS
Tensile Strength, Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	7,700 psi	6,900 psi	53 MPa	48 MPa
Tensile Modulus (Type 1, 0.125", 0.2"/min)	ASTM D638	190,000 psi	180,000 psi	1,310 MPa	1,241 MPa
Elongation at Break (Type 1, 0.125", 0.2"/min)	ASTM D638	9.5%	5%	9.5%	5%
Elongation at Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	6.5%	5%	6.5%	5%
Flexural Strength (Method 1, 0.05"/min)	ASTM D790	10,000 psi	8,600 psi	69 MPa	60 MPa
Flexural Modulus (Method 1, 0.05"/min)	ASTM D790	190,000 psi	180,000 psi	1,300 MPa	1,250 MPa
Flexural Strain at Break	ASTM D790	No Break	>10%	No Break	>10%

© 2018 3D Composites, LLC.  
Materials and data based on Stratasys FDM material product testing reports.

# Nylon 12™

UNCONDITIONED (DRY)\*\*

CONTINUED MECHANICAL PROPERTIES	TEST METHOD	ENGLISH		METRIC	
		XZ AXIS	ZX AXIS	XZ AXIS	ZX AXIS
IZOD impact - notched (Method A, 23°C)	ASTM D256	2.8 ft-lb/in	0.9 ft-lb/in	150 J/m	50 J/m
IZOD impact - unnotched (Method A, 23°C)	ASTM D256	>37.4 ft-lb/in	5.1 ft-lb/in	>2,000 J/m	275 J/m

THERMAL PROPERTIES	TEST METHOD	ENGLISH	METRIC
Heat Deflection (HDT) @ 66 psi annealed	ASTM D648	207°F	97°C
Heat Deflection (HDT) @ 66 psi unannealed	ASTM D649	167°F	75°C
Heat Deflection (HDT) @ 264 psi annealed	ASTM D650	180°F	82°C
Heat Deflection (HDT) @ 264 psi unannealed	ASTM D651	131°F	55°C
Melting Point	-----	352°F	178°C

OTHER	TEST METHOD	VALUE
Specific Gravity	ASTM D792	1.00
Flame Classification	UL94	HB
UL File Number	-----	E345258

- \*Conditioned = 20°C and 50% RH for 72 hours
- \*\*Unconditioned (Dry) = Direct from FDM system
- Annealed = 2 hours @ 140°C
- Unannealed = direct from FDM system